



常州隽隆复合材料有限公司  
CHANGZHOU JLON COMPOSITE CO.,LTD

FuHanYuan 1-820, New North District, Changzhou 213022, Jiangsu, China  
Tel: 86-519-89810829 Email:info@jloncomposite.com

## Certificate

Product:2116 impregnated fabric

### Test report

项 目Item	标准值Standard	实测值 Testing value	
纱种Yarn	E225	E225	
经密warp density	60±2	61	
纬密weft density	58±2	57	
面重weight (g/m <sup>2</sup> )	104±3	105	
宽度width (mm)	1270+10	1275	
厚 度thickness (mm)	0.09±0.01	0.092	
拉伸断裂强力 tensile strength (kgf/inch)	经向warp	≥25	30
	纬向weft	≥22	28
可燃物含量Loss of ignition %	0.10±0.05	0.1	
处理剂Sizing	S08	S08	
AP(cm <sup>3</sup> /cm <sup>2</sup> /s)	≤40	38	
判 定Result	合 格PASS		
保 质 期: 一年 Quality guarantee period: One year			

